



Teflon™ PTFE 807N X

Granular Fluoroplastic Resin

Product Information

Description

Teflon™ PTFE 807N X is a free-flowing PTFE granular resin designed for compression or automatic molding and ram extrusion (low back pressure). It offers an excellent combination of properties that are characteristic of Teflon™ fluoroplastic resins:

- Chemical inertness
- Exceptional dielectric properties
- Heat resistance
- Toughness and flexibility
- Low coefficient of friction
- Non-stick characteristics
- Negligible water absorption
- Excellent weather resistance

Teflon™ PTFE 807N X is a multi-purpose PTFE resin that yields high productivity due to its high fill density. It is easy to process, handle, and machine. It also has excellent end-use properties.

Typical Applications

Can be fabricated into billets for skived tape, basic shapes, and moldings.

It can be used for applications such as:

- Seals
- Valve seats
- Bearing pads
- Linings
- Gaskets
- Electrical/electronic parts

Processing

Teflon™ PTFE 807N X can be used in conventional PTFE processing techniques. In compression molding, a preform is made at room temperature and subsequently sintered at 365–380 °C (689–716 °F). Preform pressures of 20–50 MPa may be used. Mold shrinkage and tensile properties vary with preform pressure, sintering conditions, and geometry of the part.

Food Contact Compliance

Properly processed products (sintered at high temperatures common to the industry) made from Teflon™ PTFE 807N X resin can qualify for use in contact with food in compliance with FDA 21 CFR 177.1550 and European Regulation (EU) No. 10/2011. For details and information, please contact your Chemours representative.

Safety Precautions

Before processing any fluoroplastics, read the Material Safety Data Sheet, available upon request from our Customer Service Group at (844) 773-CHEM/2436 in the U.S. or (302) 773-1000 outside of the U.S. Also read the detailed information in the latest edition of the “Guide to the Safe Handling of Fluoropolymer Resins,” published by the Fluoropolymers Division of The Society of the Plastics Industry (www.fluoropolymers.org) or by PlasticsEurope (www.plasticseurope.org).

Storage and Handling

Preforming is easiest when the resin is uniformly between 21–27 °C (70–80 °F). As temperatures decline below this range, the resin will be increasingly difficult to mold without cracks and problems with condensed moisture. Higher temperatures inhibit flow and promote lumping. Storage conditions should be set accordingly. Cleanliness is a critical requirement for successful use of Teflon™ PTFE 807N X.

The white resin and high sintering temperatures cause even small foreign particles to become visible in finished moldings. Keep resin drums closed and clean. Good housekeeping and careful handling are essential.

Packaging

Teflon™ PTFE 807N X is packaged in 50-kg (110-lb) plastic boxes. For shipping convenience, orders of 600-kg (1,323-lb) (12 boxes/pallet) are recommended.

Typical Property Data for Teflon™ PTFE 807N X Granular Fluoroplastic Resin*

Property	Test Method		Unit	Typical Value
Particle Size, Average Diameter	ISO 13320	ASTM D4894	µm	550
Standard Specific Gravity	ISO 12086	ASTM D4894		2.16
Bulk Density	ISO 12086	ASTM D4894	g/L	900
Tensile Strength	ISO 12086	ASTM D4894	psi (MPa)	4786 (33.0)
Elongation at Break	ISO 12086	ASTM D4894	%	320
Melting Peak				
Initial	ISO 12086	ASTM D4894	°C (°F)	344 (651) ± 10
Second	ISO 12086	ASTM D4894	°C (°F)	327 (621) ± 10
Thermal Instability Index	ISO 12086	ASTM D4894		5
Water Content	ISO 12086	ASTM D4894	%	<0.04

Teflon™ PTFE 807N X meets the requirements of ASTM D4894-15, Type IV, Grade 2, except Tensile Strength and Elongation at Break.

*Typical properties are not suitable for specification purposes.

HOW TO USE THE TEFLON™ BRAND NAME WITH YOUR PRODUCT

Teflon™ is a registered trademark of Chemours for its brand of fluoroplastic resins, coatings, films, and dispersions. The Teflon™ brand name is licensed by Chemours in association with approved applications. Without a trademark license, customers may not identify their product with the Teflon™ brand name, as Chemours does not sell such offerings with the Teflon™ trademark. Unlicensed customers may refer to the Chemours product offering with only the Chemours name and product code number descriptor as Chemours sells its product offerings. There are no fair use rights or exhaustion of rights to use the Teflon™ trademark from buying from Chemours, a Chemours customer, or a distributor without a trademark license from Chemours.

If you are interested in applying for a trademark licensing agreement for the Teflon™ brand, please visit www.teflon.com/license

CAUTION: Do not use or resell Chemours materials in medical applications involving implantation in the human body or contact with internal bodily fluids or tissues unless agreed to by Seller in a written agreement covering such use. For further information, please contact your Chemours representative. For medical emergencies, spills, or other critical situations, call (866) 595-1473 within the United States. For those outside of the United States, call (302) 773-2000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit teflon.com/industrial

For sales and technical support contacts, visit teflon.com/industrialglobalsupport

© 2020 The Chemours Company FC, LLC. Teflon™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: K-26073

C-10141 (3/20)