

Tefzel™ ETFE HT-2162

Fluoropolymer Resin

Product Information

Description

Tefzel™ ETFE HT-2162 is a specialty fluoropolymer resin available in powder form. Compared with other grades of Tefzel™ ETFE, its most unique features are an intermediate flow rate and a balance of properties that make it suitable for a variety of processes and demanding end uses. **Table 1** shows typical property data for Tefzel™ ETFE HT-2162.

Tefzel™ ETFE HT-2162 and the other Tefzel™ ETFE fluoropolymers are melt processible, modified copolymers of ethylene and tetrafluoroethylene. They are high-performance resins that can be processed at relatively high rates, compared with other fluorocarbon resins. They are mechanically tough and offer an excellent balance of properties.

Tefzel™ ETFE HT-2162 can perform successfully in applications where other thermoplastics are lacking in mechanical toughness, broad thermal capability, ability to meet difficult environmental conditions, or limited by fabricating problems.

Properly processed products made from neat Tefzel™ ETFE HT-2162 are inert to most solvents and chemicals, hydrolytically stable, and weather-resistant. The recommended upper service temperature is 155 °C (311 °F); useful properties are retained at cryogenic ranges. The level and stability of dielectric properties are excellent. Mechanical properties include outstanding impact strength, cut-through, and abrasion resistance.

Statements, or data, regarding behavior in a flame situation are not intended to reflect hazards presented by this or any other material when under actual fire conditions.

Processing

Tefzel™ ETFE HT-2162 can be processed by conventional melt-extrusion techniques and injection, compression, transfer, and blow-molding processes. Compared with other grades of Tefzel™ ETFE, it provides intermediate processing

rates. Also, the melt viscosity of all grades of Tefzel™ ETFE is reduced with increasing shear rate, thus, permitting the use of pressure extrusions through narrow dies without requiring appreciable draw-down. Reciprocating screw injection molding machines are preferred. Corrosion-resistant metals should be used in contact with molten resin. Extruder barrels should be long, relative to diameter, to provide residence time for heating the resin to approximately 340 °C (640 °F).

Typical End Products

Tefzel™ ETFE HT-2162 is ideal for many end products, including electrical components, such as sleeving, coil forms, sockets, connectors, and switches; lab ware, such as tubing, valves, containers, and dishes; battery or instrument components that require chemical inertness; chemical service items, such as valve components, seal glands, pipe plugs, and corrugated tubing; and film.

Safety Precautions

Before using Tefzel™ ETFE HT-2162, refer to the Safety Data Sheet and the latest edition of "The Guide to the Safe Handling of Fluoropolymer Resins," published by The Society of the Plastics Industry, Inc. (www.plasticsindustry.org) or by PlasticsEurope (www.plasticseurope.org).

Open and use containers only in well-ventilated areas using local exhaust ventilation (LEV). Vapors and fumes liberated during hot processing, or from smoking tobacco or cigarettes contaminated with Tefzel™ ETFE HT-2162, may cause flu-like symptoms (chills, fever, sore throat) that may not occur until several hours after exposure and typically pass within about 24 hr. Vapors and fumes liberated during hot processing should be exhausted completely from the work area; contamination of tobacco with polymers should be avoided.

Mixtures with some finely divided metals, such as magnesium or aluminum, can be flammable or explosive under some conditions.

Storage and Handling

The properties of Tefzel™ ETFE HT-2162 resins are not affected by storage time. Ambient storage conditions should be designed to avoid airborne contamination and formation of water on the resin when removed from containers.

Packaging

Tefzel™ ETFE HT-2162 is packaged in 90.8-kg (200-lb) fiber drums.

Table 1. Typical Property Data for Tefzel™ ETFE HT-2162 Fluoropolymer Resin

Property	Test Method*	Unit	Value
Thermal			
Nominal Melting Point	D3418	°C (°F)	250 (482)
Flow Rate	D3159	g/10 min	8
Mechanical			
Tensile Strength, 23 °C (73 °F)	D638	MPa (psi)	38 (5,500)
Ultimate Elongation, 23 °C (73 °F)	D638	%	300
Specific Gravity	D792	—	1.8
Electrical			
Volume Resistivity	D257	ohm·m (ohm·cm)	1 x 10 ¹⁵ (1 x 10 ¹⁷)
General			
Water Absorption, 24 hr	D570	%	0.007
Weather and Chemical Resistance	—	—	Excellent
Bulk Density	—	g/L	600

*ASTM method, unless otherwise specified

Note: Typical properties are not suitable for specification purposes.

Tefzel™ ETFE HT-2162 meets the requirements of ASTM D3159, Type II, Grade 1.

HOW TO USE THE TEFLON™ BRAND NAME WITH YOUR PRODUCT

Tefzel™ is a registered trademark of Chemours for its brand of ETFE fluoropolymer resins. The Tefzel™ brand name is licensed by Chemours in association with approved applications. Without a trademark license, customers may not identify their product with the Tefzel™ brand name as Chemours does not sell such offerings with the Tefzel™ trademark. Unlicensed customers may refer to the Chemours product offering with only the Chemours name and product code number descriptor as Chemours sells its product offerings. There are no fair use rights or exhaustion of rights to use the Tefzel™ trademark from buying from Chemours, a Chemours customer or a distributor without a trademark license from Chemours.

If you are interested in applying for a trademark licensing agreement for the Tefzel™ brand, please visit teflon.com/license

CAUTION: Do not use or resell Chemours materials in medical applications involving implantation in the human body or contact with internal bodily fluids or tissues unless agreed to by Seller in a written agreement covering such use. For further information, please contact your Chemours representative. For medical emergencies, spills, or other critical situations, call (866) 595-1473 within the United States. For those outside of the United States, call (302) 773-2000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit teflon.com/tefel

For sales and technical support contacts, visit teflon.com/industrialglobalsupport

© 2018 The Chemours Company FC, LLC. Teflon™, Tefzel™, and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

C-11630 (5/18)