



Teflon™ PFA

Fluoropolymer Film

Properties Bulletin

Description

Teflon™ PFA film is a transparent, thermoplastic film that can be heat sealed, thermoformed, vacuum formed, heat bonded, welded, metallized, laminated (combined with dozens of other materials), and used as an excellent hot-melt adhesive. This wide variety of fabrication possibilities combines with the following important properties to offer a unique balance of capabilities not available in any other plastic film.

Chemical Compatibility

Teflon™ PFA film is chemically inert and solvent-resistant to virtually all chemicals, except molten alkali metals, gaseous fluorine, and certain complex halogenated compounds, such as chlorine trifluoride at elevated temperatures and pressures. It also has low permeability to liquids, gases, moisture, and organic vapors.

Electrical Reliability

- Superior reliability and retention of properties over large areas of film
- High dielectric strength, over 260 kV/mm for 0.025-mm film (6500 V/mil for 1-mil film)
- No electric tracking, non-wettable, and non-charring
- Very low power factor and dielectric constant, only slight change over wide ranges of temperature and frequency

Wide Thermal Range

- Continuous service temperature: -240 to 260 °C (-400 to 500 °F)
- Melting range: 300 to 310 °C (572 to 590 °F)
- Heat sealable

Mechanical Toughness

- Superior anti-stick and low frictional properties
- High resistance to impact and tearing
- Useful physical properties at cryogenic temperatures

Long Time Weatherability*

- Inert to outdoor exposure
- High transmittance of ultraviolet and all, but far, infrared

Reliability

- Teflon™ PFA film contains no plasticizers or other foreign materials.
- Conventional equipment and techniques can be used for processing; basic composition and properties will not be influenced.
- Rigid quality control by Chemours ensures uniform gauge, void-free film.

Teflon™ PFA Film

The convenience of Teflon™ PFA fluoropolymer in easy-to-use film facilitates the design and fabrication of this low friction thermoplastic for all sorts of high performance jobs. It is transparent and can be heat sealed, thermoformed, welded, and heat bonded. Superior anti-stick properties make it an ideal release film for many applications. A cementable type with an invisible surface treatment is available for bonding to one or both sides with adhesives. This versatility is augmented by the superior properties of a true melt-processible fluoropolymer and the wide choice of product dimensions available from Chemours.

*Type C film is not recommended for outdoor use.

Table 1: Types and Gauges of Teflon™ PFA Fluoropolymer Film

Gauge	50	100	200	300	500	1000	2000	6000	9000	12500
Thickness, mil	0.5	1	2	3	5	10	20	60	90	125
Thickness, µm	12.5	25	50	75	125	250	500	1500	2250	3125
Approx. area factor, ft ² /lb	180	90	45	30	18	9	4.5	1.5	1.0	0.7
Approx. area factor, m ² /kg	36	18	9	6.4	3.8	1.9	0.95	0.3	0.2	0.15
Availability										
Type LP—PFA, general-purpose	X	X	X	X	X	X	X	X	X	X
Type CLP—PFA, one side cementable	X	—	X	—	—	—	—	—	—	—
Type CLP20—PFA, both sides cementable	X	X	X	X	X	—	—	—	—	—

Note: Each roll of Teflon™ film is clearly identified as to resin type, film thickness, and film type.

PFA: Resin type 200: Film thickness, 200 gauge, 2 mil CLP: Film type, cementable one side



Table 2: Typical Properties of Teflon™ PFA Fluoropolymer Film

Property	Test Method*	Typical Value**	
		SI Units	English Units
Mechanical			
Tensile Strength at Break	D882	21 MPa	3000 psi
Elongation at Break	D882		300%
Yield Point	D882	12 MPa	1700 psi
Elastic Modulus	D882	480 MPa	70,000 psi
Impact Resistance	Chemours pneumatic impact tester	6.2 x 10 ⁴ J/m	14 in·lb/mil
Folding Endurance (MIT)	D2176		100,000 cycles
Tear Strength—Initial (Graves)	D1004	4.90 N	500 g
Tear Strength—Propagating (Elmendorf)	D1922	0.74 N	75 g
Thermal			
Melt Point	D3418	302–310 °C	575–590 °F
Thermal Conductivity	Cenco-Fitch	0.195 W/(m·K)	1.35 Btu·in/(hr·ft ² ·°F)
Specific Heat	—	1172 J/(kg·K)	0.28 Btu/(lb·°F)
Dimensional Stability	30 min at 150 °C (302 °F)		MD = 1% shrinkage TD = 1% shrinkage
Oxygen Index	D2863		95%
Electrical			
Dielectric Strength, short-time, in air at 23 °C (73 °F), 6.35 mm (1/4 in) diameter electrode, 0.79 mm (1/32 in) radius, 60 Hz, 500 V/s rate of rise: 0.025 mm (1 mil) film	D149 Method A	260 kV/mm	6500 V/mil
Dielectric Constant, 25 °C (77 °F), 100 Hz to 1 MHz	D150		2.0
Dissipation Factor, 25 °C (77 °F), 100 Hz to 1 MHz	D150		0.0002–0.0007
Volume Resistivity, –40 to 240 °C (–40 to 464 °F)	D257		>1 x 10 ¹⁷ ohm·cm
Chemical			
Moisture Absorption	—		<0.02%
Permeability, Gas:			cm ³ /(m ² ·24 hr·atm)***
Carbon Dioxide	D1434		14 x 10 ³
Nitrogen			2.0 x 10 ³
Oxygen			6.7 x 10 ³
Permeability, Vapor:			g/(100 in ² ·24 hr)
Water	E96	g/(m ² ·d) 2	0.13
General			
Density	D1505	2150 kg/m ³	134 lb/ft ³
Coefficient of Friction Kinetic (Film-to-Steel)	D1894		0.1–0.3
Refractive Index	D542		1.350
Solar Transmission	E424		96%

*ASTM method, unless otherwise specified

**For 0.050-mm (2-mil) film at 25 °C (77 °F), unless otherwise specified

***To convert to cm³/(100 in²·24 hr·atm), multiply by 0.0645**HOW TO USE THE TEFLON™ BRAND NAME WITH YOUR PRODUCT**

Teflon™ is a registered trademark of Chemours for its brand of fluoropolymer resins, coatings, films, and dispersions. The Teflon™ brand name is licensed by Chemours in association with approved applications. Without a trademark license, customers may not identify their product with the Teflon™ brand name, as Chemours does not sell such offerings with the Teflon™ trademark. Unlicensed customers may refer to the Chemours product offering with only the Chemours name and product code number descriptor as Chemours sells its product offerings. There are no fair use rights or exhaustion of rights to use the Teflon™ trademark from buying from Chemours, a Chemours customer, or a distributor without a trademark license from Chemours.

If you are interested in applying for a trademark licensing agreement for the Teflon™ brand, please visit www.teflon.com/license

CAUTION: Do not use or resell Chemours materials in medical applications involving implantation in the human body or contact with internal bodily fluids or tissues unless agreed to by Seller in a written agreement covering such use. For further information, please contact your Chemours representative. For medical emergencies, spills, or other critical situations, call (866) 595-1473 within the United States. For those outside of the United States, call (302) 773-2000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit teflon.com/industrial For sales and technical support contacts, visit teflon.com/industrialglobalsupport

© 2020 The Chemours Company FC, LLC. Teflon™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company. Replaces: K-26944 C-10134 (7/20)